

Material Safety Data Sheet Cover-Sheet – This page provides additional New Zealand specific information for this product and must be read in conjunction with the Safety Data Sheet (SDS) attached

Product Name:	Maxima Krom Alginate Plus
Supplier:	Henry Schein
SDS Expiry:	2 June 2027
Supplier Details:	Henry Schein New Zealand 243-249 Bush Road, Rosedale, Auckland, 0632 PO Box 101 140, North Shore, Auckland 0745 Ph. 0800 808 855 www.henryschein.co.nz
Emergency Contacts:	Poisons/Hazardous Chemical Info Centre – 0800POISON/0800764766 (24 Hours) Phone 111 for Fire, Ambulance or Police
HSNO Class/Category:	6
HSNO Group Standard:	Dental Products Subsidiary Hazard Group Standard 2020 HSR002558
Statements/Pictograms:	As per attached Safety Data Sheet (SDS)
Date Prepared:	This coversheet was prepared – March 2025

This SDS coversheet has been produced by Henry Schein NZ and has been prepared in accordance with NZ EPA advice on making overseas SDS compliant to HSNO Act. The above information is based on the present state of our knowledge of the product at the time of publication. It is given in good faith, no warranty is implied with respect to the quality or the specifications of the product. Users must satisfy that the product is entirely suitable for their purpose. The SDS and this coversheet may be revised from time to time, please ensure you have a current copy.



Henry Schein

Chemwatch: 5544-06

Chemwatch Hazard Alert Code: 2

Issue Date: 02/06/2022 Print Date: 22/02/2023 L.GHS.AUS.EN.E

Versio	on No: 2.1			
Safet	Data Sheet according to WHS Regulations	(Hazardous Chemicals)	Amendment 2020 and ADG	requirements

SECTION 1 Identification of the substance / mixture and of the company / undertaking

Product Identifier

Product name	Maxima Krom Alginate Plus
Chemical Name	Not Applicable
Synonyms	Not Available
Chemical formula	Not Applicable
Other means of identification	Not Available

Relevant identified uses of the substance or mixture and uses advised against

Relevant identified uses	Use according to manufacturer's directions.
--------------------------	---

Details of the manufacturer or supplier of the safety data sheet

Registered company name	Henry Schein	
Address	189 – O'RIORDAN STREET Mascot NSW 2020 Australia	
Telephone	+61 1300 65 88 22	
Fax	1300 65 88 10	
Website	http://henryschein.com.au	
Email	customer.care@henryschein.com.au	

Emergency telephone number

Association / Organisation	Poison Information Centre
Emergency telephone numbers	13 11 26 (24 hours)
Other emergency telephone numbers	Not Available

SECTION 2 Hazards identification

Classification of the substance or mixture

Poisons Schedule	S6	
Classification [1]	ication ^[1] Sensitisation (Skin) Category 1, Serious Eye Damage/Eye Irritation Category 2A, Germ Cell Mutagenicity Category 2	
Legend:	1. Classified by Chemwatch; 2. Classification drawn from HCIS; 3. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI	

Label elements



Hazard statement(s)

H317	May cause an allergic skin reaction.
H319	Causes serious eye irritation.
H341	Suspected of causing genetic defects.

Precautionary statement(s) Prevention

P201	Obtain special instructions before use.
P280	Wear protective gloves, protective clothing, eye protection and face protection.
P261	Avoid breathing dust/fumes.
P264	Wash all exposed external body areas thoroughly after handling.
P272	Contaminated work clothing should not be allowed out of the workplace.

Precautionary statement(s) Response

P308+P313	IF exposed or concerned: Get medical advice/ attention.	
P302+P352	IF ON SKIN: Wash with plenty of water and soap.	
P305+P351+P338	IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.	
P333+P313	If skin irritation or rash occurs: Get medical advice/attention.	
P337+P313	If eye irritation persists: Get medical advice/attention.	
P362+P364 Take off contaminated clothing and wash it before reuse.		

Precautionary statement(s) Storage

P405 Store locked up.

Precautionary statement(s) Disposal

P501 Dispose of contents/container to authorised hazardous or special waste collection point in accordance with any local regulation.

SECTION 3 Composition / information on ingredients

Substances

See section below for composition of Mixtures

Mixtures

CAS No	%[weight]	Name
16919-27-0	1-2.5	potassium hexafluorotitanate(IV)
1309-48-4.	0.1-2.5	magnesium oxide
Legend: 1. Classified by Chemwatch; 2. Classification drawn from HCIS; 3. Classification drawn from Regulation (EU) No 1272/2008 - Annex VI; 4. Classification drawn from C&L * EU IOELVs available		

SECTION 4 First aid measures

Description of first aid measures

Eye Contact	 If this product comes in contact with the eyes: Wash out immediately with fresh running water. Ensure complete irrigation of the eye by keeping eyelids apart and away from eye and moving the eyelids by occasionally lifting the upper and lower lids. Seek medical attention without delay; if pain persists or recurs seek medical attention. Removal of contact lenses after an eye injury should only be undertaken by skilled personnel.
Skin Contact	 If skin contact occurs: Immediately remove all contaminated clothing, including footwear. Flush skin and hair with running water (and soap if available). Seek medical attention in event of irritation.
Inhalation	 If fumes, aerosols or combustion products are inhaled remove from contaminated area. Other measures are usually unnecessary.
Ingestion	 For advice, contact a Poisons Information Centre or a doctor at once. Urgent hospital treatment is likely to be needed.

If swallowed do NOT induce vomiting.
If vomiting occurs, lean patient forward or place on left side (head-down position, if possible) to maintain open airway and
prevent aspiration.
Observe the patient carefully.
Never give liquid to a person showing signs of being sleepy or with reduced awareness; i.e. becoming unconscious.
Give water to rinse out mouth, then provide liquid slowly and as much as casualty can comfortably drink.
Transport to hospital or doctor without delay.

Indication of any immediate medical attention and special treatment needed

Treat symptomatically.

SECTION 5 Firefighting measures

Extinguishing media

- There is no restriction on the type of extinguisher which may be used.
- Use extinguishing media suitable for surrounding area.

Special hazards arising from the substrate or mixture

Fire Incompatibility	None known.

Advice for firefighters

Fire Fighting	 Alert Fire Brigade and tell them location and nature of hazard. Wear breathing apparatus plus protective gloves in the event of a fire. Prevent, by any means available, spillage from entering drains or water courses. Use fire fighting procedures suitable for surrounding area. DO NOT approach containers suspected to be hot. Cool fire exposed containers with water spray from a protected location. If safe to do so, remove containers from path of fire. Equipment should be thoroughly decontaminated after use.
Fire/Explosion Hazard	 Non combustible. Not considered a significant fire risk, however containers may burn. Decomposition may produce toxic fumes of: metal oxides May emit poisonous fumes. May emit corrosive fumes.
HAZCHEM	Not Applicable

SECTION 6 Accidental release measures

Personal precautions, protective equipment and emergency procedures

See section 8

Environmental precautions

See section 12

Methods and material for containment and cleaning up

Minor Spills	 Clean up all spills immediately. Avoid breathing dust and contact with skin and eyes. Wear protective clothing, gloves, safety glasses and dust respirator. Use dry clean up procedures and avoid generating dust. Sweep up, shovel up or Vacuum up (consider explosion-proof machines designed to be grounded during storage and use). Place spilled material in clean, dry, sealable, labelled container.
Major Spills	 Moderate hazard. CAUTION: Advise personnel in area. Alert Emergency Services and tell them location and nature of hazard. Control personal contact by wearing protective clothing. Prevent, by any means available, spillage from entering drains or water courses. Recover product wherever possible. IF DRY: Use dry clean up procedures and avoid generating dust. Collect residues and place in sealed plastic bags or other containers for disposal. ALWAYS: Wash area down with large amounts of water and prevent runoff into drains.
	Continued

• If contamination of drains or waterways occurs, advise Emergency Services.

Personal Protective Equipment advice is contained in Section 8 of the SDS.

SECTION 7 Handling and storage

Precautions for safe handling

Safe handling	 Avoid all personal contact, including inhalation. Wear protective clothing when risk of exposure occurs. Use in a well-ventilated area. Prevent concentration in hollows and sumps. DO NOT enter confined spaces until atmosphere has been checked. DO NOT allow material to contact humans, exposed food or food utensils. Avoid contact with incompatible materials. When handling, DO NOT eat, drink or smoke. Keep containers securely sealed when not in use. Avoid physical damage to containers. Always wash hands with soap and water after handling. Work clothes should be laundered separately. Launder contaminated clothing before re-use. Use good occupational work practice. Observe manufacturer's storage and handling recommendations contained within this SDS. Atmosphere should be regularly checked against established exposure standards to ensure safe working conditions are maintained.
Other information	 Store in original containers. Keep containers securely sealed. Store in a cool, dry area protected from environmental extremes. Store away from incompatible materials and foodstuff containers. Protect containers against physical damage and check regularly for leaks. Observe manufacturer's storage and handling recommendations contained within this SDS. For major quantities: Consider storage in bunded areas - ensure storage areas are isolated from sources of community water (including stormwater, ground water, lakes and streams). Ensure that accidental discharge to air or water is the subject of a contingency disaster management plan; this may require consultation with local authorities.

Conditions for safe storage, including any incompatibilities

Suitable container	 Polyethylene or polypropylene container. Check all containers are clearly labelled and free from leaks.
Storage incompatibility	 Metals and their oxides or salts may react violently with chlorine trifluoride and bromine trifluoride. These trifluorides are hypergolic oxidisers. They ignite on contact (without external source of heat or ignition) with recognised fuels - contact with these materials, following an ambient or slightly elevated temperature, is often violent and may produce ignition. The state of subdivision may affect the results.

SECTION 8 Exposure controls / personal protection

Control parameters

Occupational Exposure Limits (OEL)	
------------------------------------	--

INGREDIENT DATA						
Source	Ingredient	Material name	TWA	STEL	Peak	Notes
Australia Exposure Standards	magnesium oxide	Magnesium oxide (fume)	10 mg/m3	Not Available	Not Available	Not Available

Emergency Limits

Ingredient	TEEL-1	TEEL-2		TEEL-3
magnesium oxide	30 mg/m3	mg/m3 120 mg/m3		730 mg/m3
Ingredient	Original IDLH		Revised IDLH	
potassium hexafluorotitanate(IV)	Not Available		Not Available	
magnesium oxide	750 mg/m3		Not Available	

Ingredient

Skin protection

Hands/feet protection

See Hand protection below

NOTE:

Occupational Exposure Band Limit

Maxima Krom Alginate Plus

Occupational Exposure Band Rating

•					
potassium hexafluorotitanate(IV)	E ≤ 0.01 mg/m ³				
Notes:	Occupational exposure banding is a process of assigning chemicals into specific categories or bands based on a chemical's potency and the adverse health outcomes associated with exposure. The output of this process is an occupational exposure band (OEB), which corresponds to a range of exposure concentrations that are expected to protect worker health.				
MATERIAL DATA					
xposure controls					
Appropriate engineering controls	Engineering controls are used to remove a hazard or place a barrier between the worker and the hazard. Well-designed engineering controls can be highly effective in protecting workers and will typically be independent of worker interactions to provide this high level of protection. The basic types of engineering controls are: Process controls which involve changing the way a job activity or process is done to reduce the risk. Enclosure and/or isolation of emission source which keeps a selected hazard "physically" away from the worker and ventilation that strategically "adds" and "removes" air in the work environment. Ventilation can remove or dilute an air contaminant if designed properly. The design of a ventilation system must match the particular process and chemical or contaminant in use. Employers may need to use multiple types of controls to prevent employee overexposure. Local exhaust ventilation is required where solids are handled as powders or crystals; even when particulates are relatively large, a certain proportion will be powdered by mutual friction. If in spite of local exhaust an adverse concentration of the substance in air could occur, respiratory protection should be considered. Such protection might consist of: (a): particle dust respirators, if necessary, combined with an absorption cartridge; (b): filter respirators with absorption cartridge or canister of the right type: (c): fresh-air hoods or masks. Air contaminants generated in the workplace possess varying "escape" velocities which, in turn, determine the "capture velocities" of fresh circulating air required to effectively remove the contam				
	3: Intermittent, low production.	3: High production, heavy use			
	4: Large hood or large air mass in motion 4: Small hood-local control only Simple theory shows that air velocity falls rapidly with distance away from the opening of a simple extraction pipe. Velocity generally decreases with the square of distance from the extraction point (in simple cases). Therefore the air speed at the extraction point should be adjusted, accordingly, after reference to distance from the contaminating source. The air velocity at the extraction fan, for example, should be a minimum of 4-10 m/s (800-2000 f/min) for extraction of crusher dusts generated 2 metres distant from the extraction point. Other mechanical considerations, producing performance deficits within the extraction apparatus, make it essential that theoretical air velocities are multiplied by factors of 10 or more when extraction systems are installed or used.				
Individual protection measures, such as personal protective equipment					
Eye and face protection	 Safety glasses with side shields. Chemical goggles. Contact lenses may pose a special hazard; soft contact lenses may absorb and concentrate irritants. A written policy document, describing the wearing of lenses or restrictions on use, should be created for each workplace or task. This should include a review of lens absorption and adsorption for the class of chemicals in use and an account of injury experience. Medical and first-aid personnel should be trained in their removal and suitable equipment should be readily available. In the event of chemical exposure, begin eye irrigation immediately and remove contact lens as soon as practicable. Lens should be removed at the first signs of eye redness or irritation - lens should be removed in a clean environment only after workers 				

have washed hands thoroughly. [CDC NIOSH Current Intelligence Bulletin 59], [AS/NZS 1336 or national equivalent]

 protective equipment, to avoid all possible skin contact. Contaminated learner items, such as heres, hells and watch-bands should be removed and destroyed. The selection of suitable glows does not only depend on the material, but also on further marks of quality which vary from manufacturer to manufacturer. Where the chemical is a preparation of several substances, the resistance of the glowe material can not be calculated in advance and has therefore to be checked prior to the application. The acad brack through time for substances has to be obtained from the manufacturer of the protective glowes and has to be obtained for the manufacture of the protective glowes and has to be obtained be washed and dired throughly. Application of a non-perfumed mostilitier is accommended. Suitability and durability of glowe type is dependent on usage. Important factors in the selection of glowes include: infequency and duratation of contact, chemical teststance of glowe material, glowe thickness and dottentify Select glowes tested to a relevant standard (e.g. Europe EN 374, US F739, ASINZS 2161.1 or national equivalent). When protoged or frequently repeated contact may occur, a glove with a protection leads of so thigher (breakthrough time greater than 240 minutes according to EN 374, ASINZS 2111.0 or national equivalent) is recommended. When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 240 minutes according to EN 374, ASINZS 2111.0 or national equivalent) is recommended. Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-ferm usa. Contaminated glowes should be reglaced. As defined in ASINT F739.96 in any spuelation, glowe are rated as: Excellent when breakthrough time > 20 min For general application, glowe with a thickness typically greater tha		
 The selection of suitable gloves does not only depend on the material, but also on further marks of quality which vary from material material to a calculated in advance and has therefore to be checked prior to the application. The exact break through time for substances has to be obtained from the manufacturer of the protective gloves and has to be observed when making a final choice. Personal hygiane is a key element of effective hand care. Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried throughly. Application of an on-perfured metisturiser is recommended. Suitability and durability of glove type is dependent on usage. Important factors in the selection of gloves include: • frequency and duration of contact. • othernical resistance of glove material. • othernical resistance of glove material. • glove thickness and • dosterity Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent). • When protonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. • Othernical is expected, a glove with a protection class of 5 or higher (breakthrough time greater than 450 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent). • When protonged to regulate the selection glove are rated as: • accelent when breakthrough time > 20 min • Boar when breakthrough time > 20 min •		
manufacturer to manufacturer. Where the chemical is a proparation of several substances, the resistance of the glove material can not be calculated in advance and that herefore to be checked prior to the application. The exact break through time for substances has to be obtained from the manufacturer of the protective gloves and has to be observed when making a final choice. Personal hygines is a key element of affective hand care. Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried throughly. Application of a non-perfumed molsturier is recommended. Suitability and duration of contact. • Thequency and duration of contact. • Inequency and duration of contact. • Inequency and duration of contact. • glove hickness and • datafrity Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent). • When prolonged or foreguently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.10 r national equivalent). • When only bird forotact is expected, a glove with a protection dass of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.10 r national equivalent) is recommended. • When only bird forotact is expected, a glove with a protection dass of 5 or higher (breakthrough time coording to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. • Contaminated gloves should be replaced. As defined in AS/TM F739-96 in may application, gloves are nated as: • Excellent when breakthrough time > 20 min • Good when breakthrough time > 20 min • Fair when breakthrough time > 20 min • Fair when breakthrough time > 20 min • Fair when breakthrough time > 20 min • Glove material dgrades • For general applications, gloves with a thickness in an throases may be required for glove material. Therefore, the manufactures technical data should always be taken into accomption of the glove material. Therefore, glo		
 can not be calculated in advance and has therefore to be checked prior to the application. The exact break through time for substances has to be obtained from the manufacturer of the protective gloves and has to be observed when making a final choice. Personal hygien is a key idement of effective hand care. Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried throughly. Application of a non-perfured moisturiser is recommended. Suitability and durability of glove type is dependent on usage. Important factors in the selection of gloves include: if-frequency and duration of contact. chemical resistance of glove material, glove thickness and deve thickness and deve thickness and deve thickness and when prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASINZS 2161.10.1 or national equivalent). When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, ASINZS 2161.10.1 or national equivalent) is recommended. Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: Evolent when breakthrough time < 20 min Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. Hourd be emphased that glove was what an inductors in tho accut or digiver resistance to a specific chemical, as the permention efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, the manufactures (to will also be based do no consideration of the aska		
The exact break through time for substances has to be obtained from the manufacturer of the protective gloves and has to be obtained when making a final choice. Personal hygiene is a key element of effective hand care. Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Suitability and duration of contact, - chemical resistance of glove material, - glove thickness and - dworthy Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent): - When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.0.1 or national equivalent): - When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.0.1 or national equivalent): is recommended. - When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 400 minutes according to EN 374, AS/NZS 2161.0.1 or national equivalent): is recommended. - Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. - Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: - Excellent when breakthrough time > 20 min - Fair when breakthrough time > 20 min - Thiore gloves (down to 1, mor release the dependent on the exact composition of hey ore material. Therefore, the manufactures tested on consideration of the task requirements and knowledge of breakthrough times. - Bore when glove and that glove thickness in no		
 observed when making a final choice. Personal hygiene is a key element of effective hand care. Gloves must only be worm on clean hands. After using gloves, hands should be washed and dried throughly. Application of a non-perfumed moisturiser is recommended. Suitability and durability of glove type is dependent on usage. Important factors in the selection of gloves include: • frequency and duration of contact, • chemical resistance of glove material, • gloves tasted to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent). • When only brief contact is expected. • Store glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. • Contaminated gloves should be replaced. • As defined in ASTM F7339-68 in any application, gloves are rated as: • Excellent when breaktmough time > 400 mint • Good when breaktmough time > 20 mint • Fair when breaktmough time > 20 mint • Fair when glove material degradas • Foor when glove material degradas • Good when breaktmough time > 20 mint • Boot which seader on consideration of the case composition of the glove waterial. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the glove will be dependent on the exact composition of the glove waterial. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the glove will be dependent on the exact composition of the glove waterial. Therefore, the manufacturers technical data should always be taken into account of engine waterial. Therefore, the manufacturers technical data should always be taken into		
 Personal hygiene is a key element of effective hand care. Gloves must only be worn on clean hands. After using gloves, hands should be washed and driad throoughly. Application of a non-perfumed moisturiser is recommended. Suitability and durability of give type is dependent on usage. Important factors in the selection of gloves include: frequency and duration of contact. chemical resistance of glove material. glove thickness and dexterity Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, ASINZS 2161.1 or national equivalent). When prolonged or frequently repeated contact may occur, a glove with a protection dass of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASINZS 2161.10.1 or national equivalent) is recommended. When only brief contact is expected. a glove with a protection class of 3 or higher (breakthrough time greater than 200 minutes according to EN 374, ASINZS 161.10.1 or national equivalent) is recommended. Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-ferm use. Contaminated gloves should be replaced. A defined in ASTM F739-96 in any application, gloves are rated as: Excellent when breakthrough time > 20 min Fair when breakthrough time > 20 min Fair when breakthrough time > 20 min For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove material. Therefore, glove selection should also be based on consideration of the sake must and show by and the gloves material. For general applications, gloves with a thickness is not necessarily a good predictor of glove material. Therefore, glove selection of the task. Requirements and knowledge of breakthrough		
 should be washed and dired throughly. Application of a non-perfund molistirer is recommended. Suitability and durability of giove type is dependent on usage. Important factors in the selection of gioves include: frequency and duration of contect. chemical resistance of giove material. giove thickness and dexterity Select gioves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/N25 2161.1 or national equivalent). When prolonged or frequently repeated contact may occur: a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/N25 2161.10.1 or national equivalent) is recommended. When only bird contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/N25 2161.10.1 or national equivalent) is recommended. Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. Contaminated gloves should be replaced. Xa defined in ASTM F-739-80 in any application, gloves are rated as: Excellent when breakthrough time > 400 min Good when breakthrough time > 20 min Fair when breakthrough time > 20 min For general applications, gloves with a thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permetation efficiency of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness way also vary depending on the glove material. Therefore, glove selection should also be based on consideration or the task requirements and knowledge of breakthrough times. Glove thickness way also vary depending on the glove material. Therefore, glove selection should also be based on consideration protection and would no		-
Suitability and durability of glove type is dependent on usage. Important factors in the selection of gloves include: • frequency and durability of glove type is dependent on usage. Important factors in the selection of gloves include: • detering • glove thickness and • detering Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, ASNZS 2161.1 or national equivalent). • When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent) is recommended. • When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 240 minutes according to EN 374, ASNZS 2161.10.1 or national equivalent) is recommended. • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. • Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: • Excellent when breakthrough time > 20 min • Fair when breakthrough time > 20 min • Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasized that gloves with a thickness typically greater than 0.35 mm, are recommended. It should be beaded on consideration of the tax requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove material. Therefore, glove selection should also be based on consideration of the tax requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should laways be taken into account to ensure salection of the most approprinte gloves for the task. Net: Depending on the activity being conducted, gloves of varijny th		
 frequency and duration of contact. chemical resistance of glove material, glove thickness and dextrity Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent). When protonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 50 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: Excellent when breakthrough time > 400 min Good when breakthrough time > 20 min Fair when breakthrough time > 420 min Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the prevation of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the glove and the glove and the glove and ploted tors, prove selection of the glove material case. For example: Thinner gloves (plot 03 mm or less) may be required where a high degree of manual destarily is needed. However, these gloves are only likely to give short duraton protection and would normally be gue applications, then disposed d. Thicker gloves (plot 03 mm or nero) may be required where a high degree of manual destarily is needed. Howeve		
 chemical resistance of glove material, glove blickness and dextority Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent). When prolonged or frequently repeated contact may occur, a glove with a protection class of 3 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. Contaminated gloves should be replaced. As defined in ASTM F.739-96 in any application, gloves are rated as: Excellent when breakthrough time > 420 min Good when breakthrough time > 20 min Par when breakthrough time > 20 min Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove material degrades Glove thickness may also vary depending on the cake requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to emsure selection of the most appropriate glove of or the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required to repetific tasks. For example: Tinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed.		
 glove thickness and dexterily Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent). When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: Excellent when breakthrough time > 20 min Good when breakthrough time > 20 min Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasized that glove thickness is not necessarily a good predictor of glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove thickness. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterily is needed. However, these gloves selection or how on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfurmed misture potential Glove thickness may also vary depending on the glove materials for protection against undissolved, dry solids, where abrasion or puncture potential Gloves thickness may also vary depending on the gloves of varying thickness may be required for specific tasks		
 · dexterily Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent). · When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. · When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. · Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. · Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: · Excellent when breakthrough time > 20 min · Good when breakthrough time > 20 min · Fair when breakthrough time > 20 min · Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. · Thinker gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterily is needed. However, these gloves are only likely to give short duration protection adwoid normally be isoft of a more specific tasks. For example: · Thinker gloves (down to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worm on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfurmed moisturiser is recommended. · Thinker gloves (up		
Select gloves tested to a relevant standard (e.g. Europe EN 374, US F739, AS/NZS 2161.1 or national equivalent). • When prolonged or frequently repeated contact may occur, a glove with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZS 2161.1.0 r antional equivalent) is recommended. • When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/NZS 2161.1.0.1 or national equivalent) is recommended. • Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. • Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: • Excellent when breakthrough time > 480 min • God when breakthrough time > 20 min • Fair when breakthrough time > 20 min • Fair when breakthrough time > 20 min • For when glove muterial degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permetion efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, the manufactures technical data should always be taken into account to ensus expecific acks. For example: • Thinner gloves (down to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where three is abroid where years and would out onmally be is for single expected. However, these gloves (the 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where three is abroid own to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where three is abraison or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be ashed and dried thoroughly. Applicatio		
 When prolonged or frequently repeated contact may occur, a glow with a protection class of 5 or higher (breakthrough time greater than 240 minutes according to EN 374, AS/NZ5 2161.0.1 or national equivalent) is recommended. When only bief contact is expected, a glow with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/NZ5 2161.1.0 or national equivalent) is recommended. Some glove polyme types are less affected by movement and this should be taken into account when considering gloves for long-term use. Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: Excellent when breakthrough time > 20 min Good when breakthrough time > 20 min Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of avaing thickness may be required efficiency of a manufacturers technical (as well as a chemical), risk ley were for annual ducterity is needed. However, these gloves are only likely to give short duration protection and would normally be required for specific takes. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual ducterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use aphlications, then disposed of. Thinner gloves (down too 1.1 mm or less) may be required where a high degree of manual		
 greater than 240 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: Excellent when breakthrough time > 480 min Good when breakthrough time > 20 min Fair when breakthrough time < 20 min Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required where a high degree of manual dexterily is needed. However, these gloves use to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Glove thickness that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abraise particles are not present. Polychioroprene. Thinker g		
 When only brief contact is expected, a glove with a protection class of 3 or higher (breakthrough time greater than 60 minutes according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: Excellent when breakthrough time > 480 min Good when breakthrough time > 20 min Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove maturfacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dextertly is needed. However, these gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abraisve particles are not present. polychloroprene. hinitie rubber. butyl rubber. buty		
according to EN 374, AS/NZS 2161.10.1 or national equivalent) is recommended. Some glove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: Excellent when breakthrough time > 20 min Good when breakthrough time > 20 min Fair when breakthrough time > 20 min Fair when breakthrough time > 20 min For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove model. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove montacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required thorsey. Thinner gloves (glow to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfunded most appropriate is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. butyl rubber		
 Some jove polymer types are less affected by movement and this should be taken into account when considering gloves for long-term use. Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: Excellent when breakthrough time > 480 min Good when breakthrough time > 20 min Fair when breakthrough time > 20 min Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is a barasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abraive particles on threesent. polychloroprene. hutti rubber. polychloroprene. <l< th=""><th></th><th></th></l<>		
long-term use. • Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: • Excellent when breakthrough time > 480 min • Good when breakthrough time > 20 min • Fair when breakthrough time > 20 min • Por when glove material degrades • For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove soft varying thickness may be required tor specific tasks. For example: • Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dextrify is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, there there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. • buly/olhoroprene. • nitrile rubber. • hitrile rubber. • buly/inyli chloride. </th <th></th> <th></th>		
 Contaminated gloves should be replaced. As defined in ASTM F-739-96 in any application, gloves are rated as: Excellent when breakthrough time > 480 min Good when breakthrough time > 20 min Fair when breakthrough time > 20 min Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required dors pecific tasks. For example: Thinner gloves (up to 3 mm or more) may be required where a high degree of manual detartiys in eeeded. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves thus the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. hitrile rubber. bulyf rubber. bulyf rubber. bulyf rubber. polychloroprene. polyvinyl chioride. 		
As defined in ASTM F-739-96 in any application, gloves are rated as: Excellent when breakthrough time > 480 min Good when breakthrough time > 20 min Fair when breakthrough time > 20 min Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove mature selection of the most appropriate glove for the tasks. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where tare is a mechanical (as well as a chemical) risk i.e. where there is a brasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. nitrile rubber. butyl rubber. butylicknese. 		-
 Excellent when breakthrough time > 480 min Good when breakthrough time > 20 min Fair when breakthrough time < 20 min Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychoroprene. initrile rubber. butyl rubber. butyl rubber. butyl rubber. butyl rubber. polyvinyl chloride. 		
 Good when breakthrough time > 20 min Fair when breakthrough time > 20 min Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. nitrile rubber. butyl rubber. butyl rubber. butyl rubber. polychloroprene. polychloroprene. polychloroprene. polychloroprene. polychloroprene. polychlor		
 Fair when breakthrough time < 20 min Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove material of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. nitrile rubber. butyl rubber. butyl rubber. butyl rubber. polyvinyl chloride. 		
 Poor when glove material degrades For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. intitie rubber. butyl rubber. butyl rubber. fluorocaoutchouc. polyvinyl chloride. 		
For general applications, gloves with a thickness typically greater than 0.35 mm, are recommended. It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. hitrile rubber. butyl rubber. polychloroprene. hitrile rubber. polyvinyl chloride.		
It should be emphasised that glove thickness is not necessarily a good predictor of glove resistance to a specific chemical, as the permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. • polychloroprene. • polychloroprene. • polychloroprene. • butyl rubber. • butyl rubber. • butyl rubber. • polyvinyl chloride.		
 permeation efficiency of the glove will be dependent on the exact composition of the glove material. Therefore, glove selection should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. nitrile rubber. butyl rubber. fluorocaoutchouc. polyvinyl chloride. 		
 should also be based on consideration of the task requirements and knowledge of breakthrough times. Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thickner gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. butyl rubber. butyl rubber. fluorocaoutchouc. polyvinyl chloride. 		
Glove thickness may also vary depending on the glove manufacturer, the glove type and the glove model. Therefore, the manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: • Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. • Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. • polychloroprene. • nitrile rubber. • butyl rubber. • butyl rubber. • polyvinyl chloride.		
 manufacturers technical data should always be taken into account to ensure selection of the most appropriate glove for the task. Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. nitrile rubber. butyl rubber. fluorocaoutchouc. polyvinyl chloride. 		
 Note: Depending on the activity being conducted, gloves of varying thickness may be required for specific tasks. For example: Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. nitrile rubber. butyl rubber. fluorocaoutchouc. polyvinyl chloride. 		
 Thinner gloves (down to 0.1 mm or less) may be required where a high degree of manual dexterity is needed. However, these gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. nitrile rubber. butyl rubber. fluorocaoutchouc. polyvinyl chloride. 		
 gloves are only likely to give short duration protection and would normally be just for single use applications, then disposed of. Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. nitrile rubber. butyl rubber. fluorocaoutchouc. polyvinyl chloride. 		
 Thicker gloves (up to 3 mm or more) may be required where there is a mechanical (as well as a chemical) risk i.e. where there is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. nitrile rubber. butyl rubber. fluorocaoutchouc. polyvinyl chloride. 		
 is abrasion or puncture potential Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. nitrile rubber. butyl rubber. fluorocaoutchouc. polyvinyl chloride. 		
Gloves must only be worn on clean hands. After using gloves, hands should be washed and dried thoroughly. Application of a non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. initrile rubber. butyl rubber. fluorocaoutchouc. polyvinyl chloride.		
 non-perfumed moisturiser is recommended. Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. nitrile rubber. butyl rubber. fluorocaoutchouc. polyvinyl chloride. 		
 Experience indicates that the following polymers are suitable as glove materials for protection against undissolved, dry solids, where abrasive particles are not present. polychloroprene. nitrile rubber. butyl rubber. fluorocaoutchouc. polyvinyl chloride. 		
 where abrasive particles are not present. polychloroprene. nitrile rubber. butyl rubber. fluorocaoutchouc. polyvinyl chloride. 		
 polychloroprene. nitrile rubber. butyl rubber. fluorocaoutchouc. polyvinyl chloride. 		
 Initrile rubber. butyl rubber. fluorocaoutchouc. polyvinyl chloride. 		
 butyl rubber. fluorocaoutchouc. polyvinyl chloride. 		
 fluorocaoutchouc. polyvinyl chloride. 		
Polyvinyl chloride.		•
		Gloves should be examined for wear and/ or degradation constantly.
Body protection See Other protection below	Body protection	See Other protection below
P Overalls.		
P.V.C apron.		
Other protection Parrier cream.	Other protection	
 Skin cleansing cream. 		
Eye wash unit.		r Eye wash unit.

Respiratory protection

Type -P Filter of sufficient capacity. (AS/NZS 1716 & 1715, EN 143:2000 & 149:2001, ANSI Z88 or national equivalent)

Required Minimum Protection Factor	Half-Face Respirator	Full-Face Respirator	Powered Air Respirator
up to 10 x ES	P1 Air-line*		PAPR-P1 -
up to 50 x ES	Air-line**	P2	PAPR-P2
up to 100 x ES	-	P3	-
		Air-line*	-
100+ x ES	-	Air-line**	PAPR-P3

* - Negative pressure demand ** - Continuous flow

A(All classes) = Organic vapours, B AUS or B1 = Acid gasses, B2 = Acid gas or hydrogen cyanide(HCN), B3 = Acid gas or hydrogen cyanide(HCN), E = Sulfur

dioxide(SO2), G = Agricultural chemicals, K = Ammonia(NH3), Hg = Mercury, NO = Oxides of nitrogen, MB = Methyl bromide, AX = Low boiling point organic compounds(below 65 degC)

· Respirators may be necessary when engineering and administrative controls do not adequately prevent exposures.

• The decision to use respiratory protection should be based on professional judgment that takes into account toxicity information, exposure measurement data, and frequency and likelihood of the worker's exposure - ensure users are not subject to high thermal loads which may result in heat stress or distress due to personal protective equipment (powered, positive flow, full face apparatus may be an option).

· Published occupational exposure limits, where they exist, will assist in determining the adequacy of the selected respiratory protection. These may be government mandated or vendor recommended.

· Certified respirators will be useful for protecting workers from inhalation of particulates when properly selected and fit tested as part of a complete respiratory protection program.

· Where protection from nuisance levels of dusts are desired, use type N95 (US) or type P1 (EN143) dust masks. Use respirators and components tested and approved under appropriate government standards such as NIOSH (US) or CEN (EU)

· Use approved positive flow mask if significant quantities of dust becomes airborne.

· Try to avoid creating dust conditions.

Class P2 particulate filters are used for protection against mechanically and thermally generated particulates or both.

P2 is a respiratory filter rating under various international standards, Filters at least 94% of airborne particles

Suitable for:

· Relatively small particles generated by mechanical processes eg. grinding, cutting, sanding, drilling, sawing.

· Sub-micron thermally generated particles e.g. welding fumes, fertilizer and bushfire smoke.

· Biologically active airborne particles under specified infection control applications e.g. viruses, bacteria, COVID-19, SARS

SECTION 9 Physical and chemical properties

Appearance

Information on basic physical and chemical properties

White powder with pleasant odour; insoluble in water. Relative density (Water = Physical state Divided Solid Not Available 1) Partition coefficient Odour Not Available Not Available n-octanol / water Auto-ignition temperature Odour threshold Not Available Not Applicable (°C) Decomposition Not Available pH (as supplied) Not Available temperature (°C) Melting point / freezing Not Available Viscosity (cSt) Not Available point (°C) Initial boiling point and Molecular weight (g/mol) Not Available Not Applicable boiling range (°C) Flash point (°C) Not Applicable Taste Not Available Evaporation rate Not Available **Explosive properties** Not Available Flammability **Oxidising properties** Not Available Not Applicable Surface Tension (dyn/cm Upper Explosive Limit (%) Not Applicable Not Applicable or mN/m) Lower Explosive Limit (%) Volatile Component (%vol) Not Applicable Not Available Vapour pressure (kPa) Not Available Not Available Gas group Solubility in water Immiscible pH as a solution (1%) Not Available Vapour density (Air = 1) Not Available VOC g/L Not Available

SECTION 10 Stability and reactivity

Reactivity	See section 7
Chemical stability	 Unstable in the presence of incompatible materials. Product is considered stable. Hazardous polymerisation will not occur.
Possibility of hazardous reactions	See section 7
Conditions to avoid	See section 7
Incompatible materials	See section 7
Hazardous decomposition products	See section 5

SECTION 11 Toxicological information

Information on toxicological effects

Inhaled	The material is not thought to produce adverse health effects or irritation of the respiratory tract (as classified by EC Directives using animal models). Nevertheless, good hygiene practice requires that exposure be kept to a minimum and that suitable control measures be used in an occupational setting. Persons with impaired respiratory function, airway diseases and conditions such as emphysema or chronic bronchitis, may incur further disability if excessive concentrations of particulate are inhaled. If prior damage to the circulatory or nervous systems has occurred or if kidney damage has been sustained, proper screenings should be conducted on individuals who may be exposed to further risk if handling and use of the material result in excessive exposures.
Ingestion	The material has NOT been classified by EC Directives or other classification systems as "harmful by ingestion". This is because of the lack of corroborating animal or human evidence. The material may still be damaging to the health of the individual, following ingestion, especially where pre-existing organ (e.g liver, kidney) damage is evident. Present definitions of harmful or toxic substances are generally based on doses producing mortality rather than those producing morbidity (disease, ill-health). Gastrointestinal tract discomfort may produce nausea and vomiting. In an occupational setting however, ingestion of insignificant quantities is not thought to be cause for concern.
Skin Contact	 Skin contact is not thought to have harmful health effects (as classified under EC Directives); the material may still produce health damage following entry through wounds, lesions or abrasions. Limited evidence exists, or practical experience predicts, that the material either produces inflammation of the skin in a substantial number of individuals following direct contact, and/or produces significant inflammation when applied to the healthy intact skin of animals, for up to four hours, such inflammation being present twenty-four hours or more after the end of the exposure period. Skin irritation may also be present after prolonged or repeated exposure; this may result in a form of contact dermatitis (nonallergic). The dermatitis is often characterised by skin redness (erythema) and swelling (oedema) which may progress to blistering (vesiculation), scaling and thickening of the epidermis. At the microscopic level there may be intercellular oedema of the spongy layer of the skin (spongiosis) and intracellular oedema of the epidermis. Open cuts, abraded or irritated skin should not be exposed to this material Entry into the blood-stream through, for example, cuts, abrasions, puncture wounds or lesions, may produce systemic injury with harmful effects. Examine the skin prior to the use of the material and ensure that any external damage is suitably protected.
Eye	Evidence exists, or practical experience predicts, that the material may cause eye irritation in a substantial number of individuals and/or may produce significant ocular lesions which are present twenty-four hours or more after instillation into the eye(s) of experimental animals. Repeated or prolonged eye contact may cause inflammation characterised by temporary redness (similar to windburn) of the conjunctiva (conjunctivitis); temporary impairment of vision and/or other transient eye damage/ulceration may occur.
Chronic	Strong evidence exists that the substance may cause irreversible but non-lethal mutagenic effects following a single exposure. Practical experience shows that skin contact with the material is capable either of inducing a sensitisation reaction in a substantial number of individuals, and/or of producing a positive response in experimental animals. Substances that can cause occupational asthma (also known as asthmagens and respiratory sensitisers) can induce a state of specific airway hyper-responsiveness via an immunological, irritant or other mechanism. Once the airways have become hyper- responsive, further exposure to the substance, sometimes even to tiny quantities, may cause respiratory symptoms. These symptoms can range in severity from a runny nose to asthma. Not all workers who are exposed to a sensitiser will become hyper-responsive and it is impossible to identify in advance who are likely to become hyper-responsive. Substances than can cuase occupational asthma should be distinguished from substances which may trigger the symptoms of asthma in people with pre-existing air-way hyper-responsiveness. The latter substances are not classified as asthmagens or respiratory sensitisers Wherever it is reasonably practicable, exposure to substances that can cuase occupational asthma should be prevented. Where this is not possible the primary aim is to apply adequate standards of control to prevent workers from becoming hyper- responsive. Activities giving rise to short-term peak concentrations should receive particular attention when risk management is being considered. Health surveillance is appropriate for all employees exposed or liable to be exposed to a substance which may cause occupational asthma and there should be appropriate consultation with an occupational health professional over the degree of risk and level of surveillance. Limited evidence suggests that repeated or long-term occupational exposure may produce cumulative health effects involving organs or biochemical systems. P

Maxima Krom Alginate Plus	ΤΟΧΙΟΙΤΥ	IRRITATION	
	Not Available	Not Available	
potassium	ΤΟΧΙΟΙΤΥ	IRRITATION	
hexafluorotitanate(IV)	Oral (Rat) LD50: 169 mg/kg ^[2]	Not Available	
magnesium oxide	ΤΟΧΙΟΙΤΥ	IRRITATION	
	Not Available	Not Available	
Legend:	 Value obtained from Europe ECHA Registered Substances - Acute toxicity 2. Value obtained from manufacturer's SDS. Unless otherwise specified data extracted from RTECS - Register of Toxic Effect of chemical Substances 		

POTASSIUM HEXAFLUOROTITANATE(IV)	*Foseco MSDS	
POTASSIUM HEXAFLUOROTITANATE(IV) & MAGNESIUM OXIDE	The following information refers to contact allergens as a group and may not be specific to this product. Contact allergies quickly manifest themselves as contact eczema, more rarely as urticaria or Quincke's oedema. The pathogenesis of contact eczema involves a cell-mediated (T lymphocytes) immune reaction of the delayed type. Other allergic skin reactions, e.g. contact urticaria, involve antibody-mediated immune reactions. The significance of the contact allergen is not simply determined by its sensitisation potential: the distribution of the substance and the opportunities for contact with it are equally important. A weakly sensitising substance which is widely distributed can be a more important allergen than one with stronger sensitising potential with which few individuals come into contact. From a clinical point of view, substances are noteworthy if they produce an allergic test reaction in more than 1% of the persons tested. Asthma-like symptoms may continue for months or even years after exposure to the material ends. This may be due to a non-allergic condition known as reactive airways dysfunction syndrome (RADS) which can occur after exposure to high levels of highly irritating compound. Main criteria for diagnosing RADS include the absence of previous airways disease in a non-atopic individual, with sudden onset of persistent asthma-like symptoms within minutes to hours of a documented exposure to the irritant. Other criteria for diagnosis of RADS include a reversible airflow pattern on lung function tests, moderate to severe bronchial hyperreactivity on methacholine challenge testing, and the lack of minimal lymphocytic inflammation, without eosinophilia. RADS (or asthma) following an irritating inhalation is an infrequent disorder with rates related to the concentration of and duration of exposure to the irritating substance. On the other hand, industrial bronchitis is a disorder that occurs as a result of exposure due to high concentrations of irritating substance (often particles) and is complet	
Acute Toxicity	X Carcinogenicity	×
Skin Irritation/Corrosion	× Reproductivity	×
Serious Eye Damage/Irritation	STOT - Single Exposure	×
Respiratory or Skin sensitisation	✓ STOT - Repeated Exposure	×
Mutagenicity	V Aspiration Hazard	×

Legend:

SECTION 12 Ecological information

icity					
	Endpoint	Test Duration (hr)	Species	Value	Source
Maxima Krom Alginate Plus	Not Available	Not Available	Not Available	Not Available	Not Availab
	Endpoint	Test Duration (hr)	Species	Value	Sourc
	LC50	96h	Fish	172.4mg/l	2
potassium hexafluorotitanate(IV)	EC50	72h	Algae or other aquatic plants	0.646mg/l	2
nexandoronanate(iv)	EC50	48h	Crustacea	48.2mg/l	2
	EC10(ECx)	72h	Algae or other aquatic plants	0.045mg/l	2
	Endpoint	Test Duration (hr)	Species	Value	Source
magnesium oxide	Not Available	Not Available	Not Available	Not Available	Not Availat

Extracted from 1. IUCLID Toxicity Data 2. Europe ECHA Registered Substances - Ecotoxicological Information - Aquatic Toxicity

🗙 – Data either not available or does not fill the criteria for classification

🖋 – Data available to make classification

4. US EPA, Ecotox database - Aquatic Toxicity Data 5. ECETOC Aquatic Hazard Assessment Data 6. NITE (Japan) - Bioconcentration Data 7. METI (Japan) - Bioconcentration Data 8. Vendor Data

DO NOT discharge into sewer or waterways.

Persistence and degradability

Ingredient	Persistence: Water/Soil	Persistence: Air
potassium hexafluorotitanate(IV)	HIGH	HIGH

Bioaccumulative potential

Ingredient	Bioaccumulation
potassium hexafluorotitanate(IV)	LOW (LogKOW = 0.2104)

Mobility in soil

Ingredient	Mobility
potassium hexafluorotitanate(IV)	LOW (KOC = 84.33)

SECTION 13 Disposal considerations

Waste treatment methods

	Containers may still present a chemical hazard/ danger when empty.
	 Return to supplier for reuse/ recycling if possible.
	Otherwise:
	If container can not be cleaned sufficiently well to ensure that residuals do not remain or if the container cannot be used to
	store the same product, then puncture containers, to prevent re-use, and bury at an authorised landfill.
	Where possible retain label warnings and SDS and observe all notices pertaining to the product.
Product / Packaging	DO NOT allow wash water from cleaning or process equipment to enter drains.
disposal	It may be necessary to collect all wash water for treatment before disposal.
	In all cases disposal to sewer may be subject to local laws and regulations and these should be considered first.
	Where in doubt contact the responsible authority.
	Recycle wherever possible or consult manufacturer for recycling options.
	Consult State Land Waste Management Authority for disposal.
	Bury residue in an authorised landfill.
	Recycle containers if possible, or dispose of in an authorised landfill.

SECTION 14 Transport information

Labels Required	
Marine Pollutant	NO
HAZCHEM	Not Applicable

Land transport (ADG): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

Air transport (ICAO-IATA / DGR): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

Sea transport (IMDG-Code / GGVSee): NOT REGULATED FOR TRANSPORT OF DANGEROUS GOODS

Transport in bulk according to Annex II of MARPOL and the IBC code

Not Applicable

Transport in bulk in accordance with MARPOL Annex V and the IMSBC Code

Product name	Group
potassium hexafluorotitanate(IV)	Not Available
magnesium oxide	Not Available

Transport in bulk in accordance with the IGC Code

Product name	Ship Type
potassium hexafluorotitanate(IV)	Not Available
magnesium oxide	Not Available

SECTION 15 Regulatory information

Safety, health and environmental regulations / legislation specific for the substance or mixture

potassium hexafluorotitanate(IV) is found on the following regulatory lists

Australian Inventory of Industrial Chemicals (AIIC)

magnesium oxide is found on the following regulatory lists

Australian Inventory of Industrial Chemicals (AIIC)

International WHO List of Proposed Occupational Exposure Limit (OEL) Values for Manufactured Nanomaterials (MNMS)

National Inventory Status

National Inventory	Status		
Australia - AIIC / Australia Non-Industrial Use	Yes		
Canada - DSL	Yes		
Canada - NDSL	No (potassium hexafluorotitanate(IV); magnesium oxide)		
China - IECSC	Yes		
Europe - EINEC / ELINCS / NLP	Yes		
Japan - ENCS	Yes		
Korea - KECI	Yes		
New Zealand - NZIoC	Yes		
Philippines - PICCS	Yes		
USA - TSCA	Yes		
Taiwan - TCSI	Yes		
Mexico - INSQ	Yes		
Vietnam - NCI	Yes		
Russia - FBEPH	Yes		
Legend:	Yes = All CAS declared ingredients are on the inventory No = One or more of the CAS listed ingredients are not on the inventory. These ingredients may be exempt or will require registration.		

SECTION 16 Other information

Revision Date	02/06/2022
Initial Date	02/06/2022

SDS Version Summary

Version	Date of Update	Sections Updated
2.1	02/06/2022	First Aid measures - First Aid (swallowed)

Other information

Classification of the preparation and its individual components has drawn on official and authoritative sources as well as independent review by the Chemwatch Classification committee using available literature references.

The SDS is a Hazard Communication tool and should be used to assist in the Risk Assessment. Many factors determine whether the reported Hazards are Risks in the workplace or other settings. Risks may be determined by reference to Exposures Scenarios. Scale of use, frequency of use and current or available engineering controls must be considered.

Definitions and abbreviations

PC-TWA: Permissible Concentration-Time Weighted Average PC-STEL: Permissible Concentration-Short Term Exposure Limit IARC: International Agency for Research on Cancer ACGIH: American Conference of Governmental Industrial Hygienists STEL: Short Term Exposure Limit TEEL: Temporary Emergency Exposure Limit。 IDLH: Immediately Dangerous to Life or Health Concentrations ES: Exposure Standard OSF: Odour Safety Factor NOAEL :No Observed Adverse Effect Level LOAEL: Lowest Observed Adverse Effect Level TLV: Threshold Limit Value LOD: Limit Of Detection OTV: Odour Threshold Value BCF: BioConcentration Factors BEI: Biological Exposure Index AIIC: Australian Inventory of Industrial Chemicals DSL: Domestic Substances List NDSL: Non-Domestic Substances List IECSC: Inventory of Existing Chemical Substance in China EINECS: European INventory of Existing Commercial chemical Substances ELINCS: European List of Notified Chemical Substances NLP: No-Longer Polymers ENCS: Existing and New Chemical Substances Inventory KECI: Korea Existing Chemicals Inventory NZIoC: New Zealand Inventory of Chemicals PICCS: Philippine Inventory of Chemicals and Chemical Substances TSCA: Toxic Substances Control Act TCSI: Taiwan Chemical Substance Inventory INSQ: Inventario Nacional de Sustancias Químicas NCI: National Chemical Inventory FBEPH: Russian Register of Potentially Hazardous Chemical and Biological Substances

This document is copyright.

Apart from any fair dealing for the purposes of private study, research, review or criticism, as permitted under the Copyright Act, no part may be reproduced by any process without written permission from CHEMWATCH.

TEL (+61 3) 9572 4700.